



# 272 Mortar

DS-259.0-1216

**Globally Proven  
Construction Solutions**



## 1. PRODUCT NAME

272 Mortar

## 2. MANUFACTURER

LATICRETE International, Inc.

1 LATICRETE Park North

Bethany, CT 06524-3423 USA

Telephone: +1.203.393.0010, ext. 235

Toll Free: 1.800.243.4788, ext. 235

Fax: +1.203.393.1684

Internet: [www.laticrete.com](http://www.laticrete.com)

## 3. PRODUCT DESCRIPTION

272 Mortar is a high performance bagged cementitious powder to be mixed with either water or latex admixture to install ceramic tile and stone using the thin-set method of installation.

### Uses

Designed for interior or exterior installation of ceramic tile and stone for walls and floors.

### Advantages

- High Tack—will hang tile without slippage
- Dual Purpose—for walls and floors
- Cleans with water
- Easy to Use—plastic, workable and long open time
- High Bond Strength—200% stronger than mastic type adhesives
- Safe—non-flammable and non-toxic during storage, application and after hardening

### Suitable Substrates

- Concrete
- Cement plaster
- Exterior glue plywood (interior only)\*
- Gypsum wall board (interior only)
- Cement terrazzo\*\*
- Cement mortar beds
- Concrete masonry
- Brick masonry

- Ceramic tile and stones\*\*
- Cement backer board\*\*\*

\* When mixed with 333 Super Flexible Additive.

\*\* When mixed with 3701 Mortar Admix.

\*\*\* Consult cement backer board manufacturer for specific installation recommendations and to verify acceptability for exterior use.

### Packaging

50 lb (22.7 kg) bag, 56 bags per pallet

**Color:** White and Grey

### Coverage

Approximately 75–90 ft <sup>2</sup> (7.0–8.4 m <sup>2</sup> ) per 50 lb (22.7 kg.) bag with 1/4" x 1/4" (6 mm x 6 mm) sq. notch
---

Approximately 55–65 ft <sup>2</sup> (5.1–6 m <sup>2</sup> ) per 50 lb (22.7 kg.) bag with 1/4" x 3/8" (6 mm x 9 mm) sq. notch
---

### Shelf Life

Factory sealed containers of this product are guaranteed to be of first quality for one (1) year<sup>^</sup> if stored off the ground in a dry area.

<sup>^</sup> High humidity will reduce the shelf life of bagged product.

### Limitations

- DO NOT apply directly to plywood, chipboard, particleboard, decorative laminates or resilient flooring.
- For veneer installations using this product, consult local building code requirements regarding limitations and installation system specifications.
- For installations over exterior glue plywood, decorative laminates or resilient flooring use with 333 Super Flexible Additive.
- Industry standards recommend the use of latex Additive for exterior installations. Use 3701 Mortar Admix for best results.
- DO NOT install tile/stone when surface temperatures are below freezing 32°F (0°C). Always use latex additives when temperatures approach freezing.
- Adhesives/mastics, mortars and grouts for ceramic tile, pavers, brick and stone are not designed as replacements for waterproofing membranes. When a waterproofing membrane is required, use a LATICRETE® Waterproofing Membrane (see Section 10 FILING SYSTEMS).
- For exterior use, fortify with 333 Super Flexible Additive or 3701 Mortar Admix.

*Note: Surfaces must be structurally sound, stable and rigid enough to support ceramic/stone tile, thin brick and similar finishes. Substrate deflection under all live, dead and impact loads, including concentrated loads, must not exceed L/360 for thin bed ceramic*

tile/brick installations or L/480 for thin bed stone installations where L=span length (except where local building codes specify more stringent deflection requirements)

### Cautions

Consult MSDS for more safety information.

- Contains portland cement and silica sand. May irritate eyes and skin. Avoid contact with eyes or prolonged contact with skin. In case of contact, flush thoroughly with water.
- DO NOT take internally. Silica sand may cause cancer or serious lung problems. Avoid breathing dust. Wear a respirator in dusty areas.
- Use LATAPOXY® 300 Adhesive for installing green marble, water sensitive stone and agglomerates and resin backed tile and stone. Refer to DS 633.0.
- Use a white mortar for white and light-colored marble and stone.
- For tile/stone applications in pools, fountains, showers or bathtubs, mix with 3701 Mortar Admix. Wait 14 days before filling with water.
- Protect finished work from traffic or damage by other trades for an extended period of time during cold weather conditions. At room temperature conditions 70°F (21°C), protect overnight.
- Keep out of reach of children.

## 4. TECHNICAL DATA

### VOC/LEED Product Information



This product has been certified for Low Chemical Emissions (ULCOM/GG UL2818) under the UL GREENGUARD Certification Program for Chemical Emissions for Building Materials, Finishes and Furnishings (UL 2818 Standard) by UL Environment.

Total VOC Content pounds/gallon (grams/liter) of product in unused form is 0.00 lb/gal (0.00 g/l).

### Applicable Standards

ANSI A118.1, ANSI A118.4 (when mixed with Latex)



This product has a cradle-to-gate (with options) Product-Specific (Type III) Environmental Product Declaration. The PCR review, life cycle assessment and declaration were independently verified by UL Environment in accordance with ISO 14025, ISO 14040 and ISO 14044.

## Performance Properties

### 272 Mortar mixed with 3701 Mortar Admix

Test	Test Method	Results	ANSI A118.4 Specification
Porcelain Tile Shear Bond, 28 day cure	ANSI A118.4-5.2.4	450-500 psi (3.1-3.4 MPa)	> 200 psi (1.37 MPa)
Porcelain Tile Water Soak Shear Bond	ANSI A118.4-5.2.3	200-300 psi (1.37-2.07 MPa)	> 150 psi (1 MPa)
Compressive Strength	ANSI A118.4-6	2300-2500 psi (15.8-17.2 MPa)	> 2500 psi (17.2 MPa)

Data from Report HR880

### 272 Mortar mixed with Water

Test	Test Method	Results	ANSI A118.4 Specification
Porcelain Tile Shear Bond, 28 day cure	ANSI A118.1-5.2.4	250-290 psi (1.72-2 MPa)	> 150 psi (1 MPa)
Compressive Strength	ANSI A118.4-6	1500-1700 psi (10.3-11.7 MPa)	N/A

Data from 061002-P-300-331

## Working Properties

### 272 Mortar mixed with 3701 Mortar Admix (70°F [21°C])

Open Time	60 minutes
Pot Life	5 hours
Time to Heavy Traffic	24 hours
Wet Density	107 lbs/ft <sup>3</sup> (1720 kg/m <sup>3</sup> )

### 272 Mortar mixed with Water (70°F [21°C])

Open Time	60 minutes
Pot Life	3 hours
Time to Heavy Traffic	24 hours
Wet Density	103 lbs/ft <sup>3</sup> (1653 kg/m <sup>3</sup> )

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

## 5. INSTALLATION

### Surface Preparation

All surfaces should be between 40°F (4°C) and 90°F (32°C) and structurally sound, clean and free of all dirt, oil, grease, paint, laitance, concrete sealers or curing compounds. Rough or uneven concrete surfaces should be made smooth with Latex Portland Cement Underlayment to provide a wood float (or better) finish. Dry, dusty concrete slabs or masonry should be dampened and excess water swept off. Installation may be made on a damp surface. New concrete slabs shall be damp cured and 28 days old before application. \*No minimum cure time for concrete slabs when thin-set mortar is mixed with 4237 Latex Additive or 3701 Mortar Additive or 333 Super Flexible Additive. All slabs must be plumb and true to within 1/4" (6 mm) in 10 ft (3 m). Expansion joints shall be provided through the tile work from all construction or expansion joints in the substrate. Follow ANSI specification A108.01-3.7 "requirements for movement joints: preparations by other trades" or TCNA detail

EJ-171 "Movement Joints—Vertical & Horizontal". Do not cover expansion joints with mortar.

1. Installer must verify that deflection under all live, dead and impact loads of interior plywood floors does not exceed industry standards of L/360 for ceramic tile and brick or L/480 for stone installations where L=span length.

2. Minimum construction for interior plywood floors. Mix 272 Mortar mixed with 333 Super Flexible Additive over Exterior Glue Plywood.

**SUBFLOOR:** 5/8" (15 mm) thick exterior glue plywood, either plain with all sheet edges blocked or tongue and groove, over bridged joints spaced 16" (400 mm) o.c. maximum; fasten plywood 6" (150 mm) o.c. along sheet ends and 8" (200 mm) o.c. along intermediate supports with 8d ring-shank, coated or hot dip galvanized nails (or screws); allow 1/8" (3 mm) between sheet ends and 1/4" (6 mm) between sheets edges; all sheet ends must be supported by a framing member; glue sheets to joints with construction adhesive

**UNDERLAYMENT:** 5/8" (15 mm) thick exterior glue plywood fastened 6" (150 mm) o.c. along sheet ends and 8" (200 mm) o.c. in the panel field (both directions) with 8d ring-shank, coated or hot dip galvanized nails (or screws); allow 1/8" (3 mm) to 1/4" (6 mm) between sheets and 1/4" (6 mm) between sheet edges and any abutting surfaces; offset underlayment joints from joints in subfloor and stagger joints between sheet ends; glue underlayment to subfloor with construction adhesive. Refer to Technical Data Sheet 152 "Bonding Ceramic Tile, Stone or Brick Over Wood Floors" for complete details.

### Mixing

Stir admix thoroughly before use. Place clean, potable water or a Latex Admix into a clean pail. Add 272 Mortar. Use approximately 1.5 – 2 gallons (5.7 – 7.6 ℓ) of water for 50 lbs (22.7 kg) of powder. Fortify with 3701 Mortar Admix or 333 Super Flexible Additive (for non-submerged areas) when installing porcelain tile, glass and stone mosaics in heavy traffic areas, and for exterior use. For tile installation over cement backer board, check with board manufacturer for compatibility—if an ANSI A118.4 thin-set is required then mix with latex additive. For rapid "Open to Traffic" installations use 101 Rapid Latex Admix. Mix by hand or with a slow speed mixer to a smooth, trowelable consistency. Allow mortar to slake for 5 – 10 minutes. Adjust consistency if necessary. Remix and apply with the proper sized notched trowel.

### Application

Apply mortar to the substrate with the flat side of the trowel, pressing firmly to work into surface. Comb on additional mortar with the notched side. Use the proper sized notched trowel to ensure full bedding of the tile. Spread as much mortar as can be covered with tile in 15–20 minutes. Back butter large tiles > 8" x 8" (>200 x 200 mm) to provide full bedding and firm support. Place tiles into wet, sticky mortar and beat in using a beating block and rubber mallet to embed tile and adjust level. Check mortar for complete coverage by periodically removing a tile and inspecting bedding mortar transfer onto back of tile. If mortar is skinned over (not sticky), remove and replace with fresh mortar.

### Grouting

Grout installation after a minimum of 24 hours curing time at 70°F (21°C). Grout with SPECTRALOCK® PRO Premium Grout†, SPECTRALOCK PRO Grout†, PERMACOLOR® Grout<sup>^</sup> mixed with

water or 1500 Sanded Grout or 1600 Unsanded Grout gauged with 1776 Grout Enhancer or with water.

**Cold Weather Note:** The setting of portland cement mortars and grouts are retarded by low temperatures. Protect finished work for an extended period when installing in cold weather. For faster setting mortar use Thin-Sets with 101 Rapid Latex Admix. Do not set tile when surface temperature is below freezing or when substrate is frozen.

**Hot Weather Note:** The evaporation of moisture in portland cement mortars is accelerated by hot, dry conditions. Apply to dampened surfaces and protect freshly spread mortar and finished work when installing in hot temperatures.

### Cleaning

Clean tools and tile work with water while mortar is fresh.

## 6. AVAILABILITY AND COST

### Availability

LATICRETE® and LATAPOXY® materials are available worldwide.

For Distributor information, call:

Toll Free: 1.800.243.4788

Telephone: +1.203.393.0010

For on-line Distributor information, visit LATICRETE at [www.laticrete.com](http://www.laticrete.com).

### Cost

Contact a LATICRETE/LATAPOXY Distributor in your area.

## 7. WARRANTY

See 10. FILING SYSTEM

DS 230.13: LATICRETE Product Warranty (United States and Canada)

## 8. MAINTENANCE

LATICRETE and LATAPOXY grouts require routine cleaning with a neutral pH soap and water. All other LATICRETE and LATAPOXY materials require no maintenance but installation performance and durability may depend on properly maintaining products supplied by other manufacturers.

## 9. TECHNICAL SERVICES

### Technical Assistance

Information is available by calling the LATICRETE Technical Service Hotline:

Toll Free: 1.800.243.4788, ext. 235

Telephone: +1.203.393.0010, ext. 235

Fax: +1.203.393.1948

### Technical and Safety Literature

To acquire technical and safety literature, please visit our website at [www.laticrete.com](http://www.laticrete.com).

## 10. FILING SYSTEM

Additional product information is available on our website at

[www.laticrete.com](http://www.laticrete.com). The following is a list of related documents:

DS 230.13: LATICRETE® Product Warranty (United States and Canada)

DS 230.1: 4237 Latex Additive

DS 231.0: 3701 Mortar Admix

DS 236.0: 9235 Waterproofing Membrane

DS 250.0: PERMACOLOR® Grout<sup>^</sup>

DS 256.0: 1500 Sanded Grout

DS 258.0: 1600 Unsanded Grout  
DS 264.0: 101 Rapid Set Latex Admix  
DS 265.0: 1776 Grout Enhancer  
DS 266.0: 333 Super Flexible Additive  
DS 633.0: LATAPOXY® 300 Adhesive  
DS 663.0: HYDRO BAN®  
DS 681.0: SPECTRALOCK® PRO Premium Grout†  
DS 685.0: SPECTRALOCK PRO Grout†  
TDS 152: "Bonding Ceramic Tile, Stone or Brick Over  
Wood Floors"

† United States Invention Patent No.: 6881768 (and other Patents).

^ United States Invention Patent No.: 6784229 (and other Patents)

---

LATICRETE International, Inc.  
One LATICRETE Park North, Bethany, CT 06524-3423 USA • 1.800.243.4788 • +1.203.393.0010 • [www.laticrete.com](http://www.laticrete.com)  
©2016 LATICRETE International, Inc. All trademarks shown are the intellectual properties of their respective owners.